



DS 1500 SYN

Synthetic vapour and radon barrier
Riwega | eternitycomfort

Technical data sheet
of 06/02/2014
Art. 02064007
Rev. 07 of 29/11/2021

Material	PP.PE.Alu.PE.PP	 EN 13984
Film	-	
Colour	White	
Roll width	1,5 m	
Roll length	50 m	
Roll weight	10 Kg	
Classification in accordance with UNI 11470 (IT)	C	
Classification in accordance with Onorm B4119/B3661 (AT)	Typ I	
Classification in accordance with SIA 232-1 (CH)	VU-VO G+R	
Conforms to DTU (FR)	31.2	

PROPERTIES	METHOD	UNITS	NOMINAL VALUE
Areal mass	EN 1849-2	g/m ²	130 (±10g/m ²)
Air layer equivalent to the vapour passage [Sd]	EN ISO 12572	m	> 1500
Water vapour diffusion [DVA]	EN ISO 12572	g/m ² / 24h	ca. 0,02
Water column	EN 20811	cm	-
Resistance to water penetration	EN 13984 (EN1928 Met.A)	-	Passed
Tensile strength MD*	EN 12311-1	N/50mm	170 (±30N/50mm)
Tensile strength CD*	EN 12311-1	N/50mm	110 (±30N/50mm)
Elongation MD*	EN 12311-1	%	60 (±15%)
Elongation CD*	EN 12311-1	%	45 (±15%)
Resistance to tearing MD*	EN 12310-1	N	75 (±15N)
Resistance to tearing CD*	EN 12310-1	N	90 (±15N)
Fire reaction	EN 13501-1	Class	E
UV-stability	-	Months	-
Temperature resistance	-	°C	-40 / +100
Radon permeability	ISO 11665-10	m ² /s	1,64 x 10 ⁻¹⁴
Durability			
Artificial ageing	EN 1926	-	Passed
Alkali resistance	EN 13984 (EN1928 Met.A)	-	Passed

Density	EN 1849-1	Kg/m ³	289
Thickness	EN 1849-2	mm	0,45
Vapour resistance coefficient [μ]	EN ISO 12572	-	6666667
Vapour permeability coefficient	-	Kg/m*s*Pa	0,00005*10-12
Thermal conductivity [λ]	-	W/mK	0,22
Specific heat	-	J/KgK	1700

* MD= Machine Direction; CD= Cross Direction.

Riwega S.r.l. reserves the possibility to review or change these technical values. The updated technical data sheet can be found on the website www.riwega.com.
This data sheet replaces the previous copy.